

## Structural Assembly Characteristics

- Fitted with a wide variety of zinc- or resin-attached end terminations, including open and closed strand and wire rope sockets, bridge sockets, and anchor sockets
- Available with spiral strand or structural wire rope
- Provided prestretched, measured, striped, and proofloaded upon request
- Used in applications such as main cables, suspender and wind cables of suspension bridges; tower guys; cable stays; supports and suspenders for cable roof structures; anchor and mooring lines

### Spiral Strand

- Arrangement of wires laid helically around a center wire to produce a symmetrical cross section
- Recommended for use as a load-carrying tension member where bending and flexibility are not major requirements
- Offers a high strength-to-weight ratio, high modulus of elasticity, and a small diameter-per-unit strength
- Manufactured to meet ASTM Specification A586
- Available with Class A, B. or C galvanized coating weights in diameters up to 5-1/2"



### SS-265™

- High strength spiral strand with a nominal strength 15% higher than traditional spiral strand
- Manufactured to meet ASTM Specification A586
- Recommended for use in all spiral strand applications
- Decreases total weight of spiral strand system due to its higher strength-to-weight ratio
- Available with Class A galvanized coating weight in diameters through 3-3/4"

### Structural Wire Rope

- Six strands laid helically around a core, such as another strand or another wire rope
- Recommended for use where bending ability is an important requirement
- Provides greater flexibility when compared with coarse strand constructions
- Manufactured to meet ASTM Specification A603
- Available with Class A, B. or C galvanized coating weights in diameters up to 7"



# Structural Assemblies

| STRAND DIAMETER<br>inches | STRAND DIAMETER<br>mm. | APPROXIMATE WEIGHT (lb./ft.)<br>SPIRAL STRAND | SS-265 | NOMINAL STRENGTH (tons) |          |          | STRAND DIAMETER |         | APPROX. WEIGHT (lb./ft.)<br>SPIRAL STRAND | SS-265 | NOMINAL STRENGTH (tons) |          |     |     |         |     |
|---------------------------|------------------------|---|--------|-------------------------|----------|----------|-----------------|---------|---|--------|-------------------------|----------|-----|-----|---------|-----|
|                           |                        |   |        | Class A                 | Class B* | Class C* | SS-265          | Class A |   |        | Class B*                | Class C* |     |     |         |     |
| 1/2                       | 13.0                   | 0.52  | --     | 15.0                    | 14.5     | 14.2     | --              | 2-5/16  | 59.0                                      | 11.2   | 11.0                    | 327      | 322 | 317 | Class A | 376 |
| 9/16                      | 14.5                   | 0.66  | --     | 19.0                    | 18.4     | 18.0     | --              | 2-3/8   | 60.0                                      | 11.7   | 11.6                    | 344      | 339 | 334 | Class A | 396 |
| 5/8                       | 16.0                   | 0.82  | --     | 24.0                    | 23.3     | 22.8     | --              | 2-7/16  | 62.0                                      | 12.5   | 12.2                    | 360      | 355 | 349 | Class A | 414 |
| 11/16                     | 18.0                   | 0.99  | --     | 29.0                    | 28.1     | 27.5     | --              | 2-1/2   | 64.0                                      | 12.8   | 12.9                    | 376      | 370 | 365 | Class A | 432 |
| 3/4                       | 19.0                   | 1.18  | 1.16   | 34.0                    | 33.0     | 32.3     | 39.1            | 2-9/16  | 65.0                                      | 13.6   | 13.6                    | 392      | 386 | 380 | Class A | 451 |
| 13/16                     | 21.0                   | 1.39  | 1.36   | 40.0                    | 38.8     | 38.0     | 46.0            | 2-5/8   | 67.0                                      | 14.5   | 14.4                    | 417      | 411 | 404 | Class A | 480 |
| 7/8                       | 22.0                   | 1.61  | 1.59   | 46.0                    | 44.6     | 43.7     | 52.9            | 2-11/16 | 68.0                                      | 15.2   | 15.0                    | 432      | 425 | 419 | Class A | 497 |
| 15/16                     | 24.0                   | 1.85  | 1.85   | 54.0                    | 52.4     | 51.3     | 62.1            | 2-3/4   | 70.0                                      | 15.9   | 15.6                    | 452      | 445 | 438 | Class A | 520 |
| 1                         | 26.0                   | 2.10  | 2.12   | 61.0                    | 59.2     | 57.9     | 70.1            | 2-7/8   | 74.0                                      | 17.4   | 17.2                    | 494      | 486 | 479 | Class A | 568 |
| 1-1/16                    | 27.0                   | 2.37  | 2.36   | 69.0                    | 66.9     | 65.5     | 79.4            | 3       | 76.0                                      | 18.9   | 18.8                    | 538      | 530 | 522 | Class A | 618 |
| 1-1/8                     | 29.0                   | 2.66  | 2.63   | 78.0                    | 75.7     | 74.1     | 89.7            | 3-1/8   | 79.0                                      | 20.5   | 20.4                    | 584      | 575 | 566 | Class A | 672 |
| 1-3/16                    | 30.0                   | 2.96  | 2.91   | 86.0                    | 83.4     | 81.7     | 98.9            | 3-1/4   | 83.0                                      | 22.2   | 21.8                    | 625      | 616 | 606 | Class A | 719 |
| 1-1/4                     | 32.0                   | 3.28  | 3.23   | 96.0                    | 94.1     | 92.2     | 110             | 3-3/8   | 86.0                                      | 23.9   | 23.6                    | 673      | 663 | 653 | Class A | 774 |
| 1-5/16                    | 33.0                   | 3.62  | 3.59   | 106                     | 104      | 102      | 122             | 3-1/2   | 89.0                                      | 25.7   | 25.5                    | 724      | 713 | 702 | Class A | 832 |
| 1-3/8                     | 35.0                   | 3.97  | 3.94   | 116                     | 114      | 111      | 133             | 3-5/8   | 92.0                                      | 27.6   | 27.1                    | 768      | 756 | 745 | Class A | 883 |
| 1-7/16                    | 37.0                   | 4.34  | 4.29   | 126                     | 123      | 121      | 145             | 3-3/4   | 96.0                                      | 29.5   | 29.4                    | 822      | 810 | 797 | Class A | 934 |
| 1-1/2                     | 38.0                   | 4.73  | 4.66   | 138                     | 135      | 132      | 158             | 3-7/8   | 99.0                                      | 31.5   | --                      | 878      | 865 | 852 | Class A | --  |
| 1-9/16                    | 40.0                   | 5.13  | 5.04   | 150                     | 147      | 144      | 172             | 4       | 103.0                                     | 33.6   | --                      | 925      | 911 | 897 | Class A | --  |
| 1-5/8                     | 42.0                   | 5.55  | 5.45   | 162                     | 159      | 155      | 186             | 4-1/8   | 105.0                                     | 35.7   | --                      | 985      | **  | **  | Class A | --  |
| 1-11/16                   | 43.0                   | 5.98  | 5.92   | 176                     | 172      | 169      | 202             | 4-1/4   | 109.0                                     | 37.9   | --                      | 1,002    | **  | **  | Class A | --  |
| 1-3/4                     | 45.0                   | 6.43  | 6.39   | 188                     | 184      | 180      | 216             | 4-3/8   | 111.0                                     | 40.2   | --                      | 1,108    | **  | **  | Class A | --  |
| 1-13/16                   | 46.0                   | 6.90  | 6.80   | 202                     | 198      | 194      | 232             | 4-1/2   | 115.0                                     | 42.5   | --                      | 1,173    | **  | **  | Class A | --  |
| 1-7/8                     | 48.0                   | 7.39  | 7.26   | 216                     | 212      | 207      | 248             | 4-5/8   | 117.0                                     | 44.9   | --                      | 1,239    | **  | **  | Class A | --  |
| 1-15/16                   | 49.0                   | 7.89  | 7.75   | 230                     | 226      | 221      | 264             | 4-3/4   | 122.0                                     | 47.4   | --                      | 1,306    | **  | **  | Class A | --  |
| 2                         | 52.0                   | 8.40  | 8.23   | 245                     | 241      | 238      | 282             | 4-7/8   | 124.0                                     | 49.9   | --                      | 1,376    | **  | **  | Class A | --  |
| 2-1/16                    | 53.0                   | 8.94  | 8.79   | 261                     | 257      | 253      | 300             | 5       | 128.0                                     | 52.5   | --                      | 1,448    | **  | **  | Class A | --  |
| 2-1/8                     | 54.0                   | 9.49  | 9.39   | 277                     | 273      | 269      | 319             | 5-1/4   | 133.0                                     | 57.9   | --                      | 1,596    | **  | **  | Class A | --  |
| 2-3/16                    | 56.0                   | 10.1  | 10.0   | 293                     | 289      | 284      | 337             | 5-1/2   | 140.0                                     | 63.5   | --                      | 1,752    | **  | **  | Class A | --  |
| 2-1/4                     | 58.0                   | 10.5  | 10.5   | 310                     | 305      | 301      | 356             |         |   |        |                         |          |     |     | Class A |     |

## Spiral Strand and SS-265

Based on Class A coatings, the minimum moduli of elasticity of the spiral strand are shown below. For heavier coatings, please consult WWV's Engineering Department.

1/2" to 2-3/16" ..... 24,000,000 psi  
 2-3/8" to 4" ..... 23,000,000 psi  
 4-1/8" & larger ..... 22,000,000 psi

\*Nominal strengths are based on furnishing Class B or Class C coating weights on the outside wires with Class A coating on the inside wires. The heavier Class B and Class C zinc coatings reduce the steel metallic area, accounting for the slightly lower nominal strengths.

\*\*For strength information, please contact WWV's Sales or Engineering Department.



# Structural Assemblies

## Structural Wire Rope

Based on Class A coatings, the minimum moduli of elasticity of the structural wire rope are shown below. For heavier coatings, or a combination of coats, please consult WWV's Engineering Department.

3/8" to 4" ..... 20,000,000 psi  
 4-1/4" to 4-3/4" ..... 19,000,000 psi  
 5" to 6" ..... 18,000,000 psi

WWV manufactures structural wire rope through 7<sup>mm</sup> diameter. For information on diameters larger than 6", please contact WWV's Engineering Department.

\*Nominal strengths are based on furnishing Class A, B or C coat throughout the wire rope. For a combination of coatings, please consult our Engineering Department for technical data.

\*\*For strength information, please contact WWV's Sales or Engineering Department.

| Rope Diameter<br>inches | mm.  | Approx.<br>Weight<br>(lb./ft.) | Metallic<br>Area<br>(in <sup>2</sup> ) | Nominal Strength (tons) |                     |                     | Rope Diameter<br>inches | mm.   | Approx.<br>Weight<br>(lb./ft.) | Metallic<br>Area<br>(in <sup>2</sup> ) | Nominal Strength (tons) |                     |                     |
|-------------------------|------|--------------------------------|--|-------------------------|---------------------|---------------------|-------------------------|-------|--------------------------------|--|-------------------------|---------------------|---------------------|
|                         |      |                                |  | Class A<br>Coating      | Class B<br>Coating* | Class C<br>Coating* |                         |       |                                |  | Class A<br>Coating      | Class B<br>Coating* | Class C<br>Coating* |
| 3/8                     | 9.5  | 0.24                           | 0.065                                  | 6.5                     | 6.2                 | 5.9                 | 2-1/4                   | 58.0  | 8.66                           | 2.420                                  | 235.0                   | 224.0               | 214.0               |
| 7/16                    | 11.5 | 0.32                           | 0.091                                  | 8.8                     | 8.4                 | 8.0                 | 2-3/8                   | 60.0  | 9.61                           | 2.69                                   | 261.0                   | 249.0               | 237.0               |
| 1/2                     | 13.0 | 0.42                           | 0.119                                  | 11.5                    | 11.0                | 10.5                | 2-1/2                   | 64.0  | 10.60                          | 2.97                                   | 288.0                   | 275.0               | 262.0               |
| 9/16                    | 14.5 | 0.53                           | 0.147                                  | 14.5                    | 13.8                | 13.2                | 2-5/8                   | 67.0  | 11.62                          | 3.27                                   | 317.0                   | 302.0               | 288.0               |
| 5/8                     | 16.0 | 0.65                           | 0.182                                  | 18.0                    | 17.2                | 16.4                | 2-3/4                   | 70.0  | 12.74                          | 3.58                                   | 347.0                   | 331.0               | 315.0               |
| 11/16                   | 18.0 | 0.79                           | 0.221                                  | 21.5                    | 20.5                | 19.5                | 2-7/8                   | 74.0  | 13.90                          | 3.91                                   | 379.0                   | 362.0               | 344.0               |
| 3/4                     | 19.0 | 0.95                           | 0.268                                  | 26.0                    | 24.8                | 23.6                | 3                       | 76.0  | 15.11                          | 4.25                                   | 412.0                   | 393.0               | 374.0               |
| 13/16                   | 21.0 | 1.10                           | 0.311                                  | 30.0                    | 28.6                | 27.3                | 3-1/4                   | 83.0  | 18.00                          | 5.04                                   | 475.0                   | 453.0               | 432.0               |
| 7/8                     | 22.0 | 1.28                           | 0.361                                  | 35.0                    | 33.4                | 31.8                | 3-1/2                   | 89.0  | 21.00                          | 5.83                                   | 555.0                   | 529.0               | 504.0               |
| 15/16                   | 24.0 | 1.47                           | 0.414                                  | 40.0                    | 38.2                | 36.4                | 3-3/4                   | 96.0  | 24.00                          | 6.67                                   | 640.0                   | 611.0               | 582.0               |
| 1                       | 26.0 | 1.67                           | 0.471                                  | 45.7                    | 43.6                | 41.5                | 4                       | 103.0 | 27.00                          | 7.59                                   | 730.0                   | 696.0               | 664.0               |
| 1-1/8                   | 29.0 | 2.11                           | 0.596                                  | 57.8                    | 55.1                | 52.5                | 4-1/4                   | 109.0 | 30.50                          | 8.58                                   | 828.0                   | **                  | **                  |
| 1-1/4                   | 32.0 | 2.64                           | 0.745                                  | 72.2                    | 68.9                | 65.6                | 4-1/2                   | 115.0 | 34.70                          | 9.62                                   | 928.0                   | **                  | **                  |
| 1-3/8                   | 35.0 | 3.21                           | 0.906                                  | 87.8                    | 83.8                | 79.8                | 4-3/4                   | 122.0 | 38.00                          | 10.74                                  | 1,036.0                 | **                  | **                  |
| 1-1/2                   | 38.0 | 3.82                           | 1.076                                  | 104.0                   | 99.2                | 94.5                | 5                       | 128.0 | 42.20                          | 11.88                                  | 1,146.0                 | **                  | **                  |
| 1-5/8                   | 42.0 | 4.51                           | 1.270                                  | 123.0                   | 117.0               | 112.0               | 5-1/4                   | 133.0 | 46.50                          | 13.09                                  | 1,263.0                 | **                  | **                  |
| 1-3/4                   | 45.0 | 5.24                           | 1.470                                  | 143.0                   | 136.0               | 130.0               | 5-1/2                   | 140.0 | 51.00                          | 14.37                                  | 1,387.0                 | **                  | **                  |
| 1-7/8                   | 48.0 | 6.03                           | 1.690                                  | 164.0                   | 156.0               | 149.0               | 5-3/4                   | 146.0 | 55.80                          | 15.70                                  | 1,515.0                 | **                  | **                  |
| 2                       | 52.0 | 6.85                           | 1.920                                  | 186.0                   | 177.0               | 169.0               | 6                       | 152.0 | 60.70                          | 17.10                                  | 1,650.0                 | **                  | **                  |
| 2-1/8                   | 54.0 | 7.73                           | 2.170                                  | 210.0                   | 200.0               | 191.0               |                         |       |                                |  |                         |                     |                     |

Note: Assemblies utilizing structural wire rope are not suitable for use in certain applications, such as where the assembly is required to operate over sheaves, drums, rollers and the like. For these types of applications, assemblies utilizing traditional wire rope constructions are used. Please consult with WWV's Engineering Department before specifying structural wire rope.



## Structural Assembly Options

*Many options are available for Bethlehem Wire Rope® Structural Assemblies. The options listed here are but a few, and by no means should be considered inclusive. In fact, WWW has designed many unique products for specific structural applications. Please consult with our Engineering Department to discuss your needs and requirements.*

### Aesthetic Options

A number of options exist for overall aesthetic appeal. End terminations may be brightly painted, and plastic-extruded coverings for cable also offer a wide variation of color in addition to providing a stain free environment where roof fabric is expected to contact the cable. WWW encourages designers, engineers and architects to contact us during design stages to discuss their ideas and requirements.

### Corrosion Protection Options

**Plastic Sheathing** — A polymeric covering may be extruded over the wire rope or strand to enhance corrosion protection.

**Z-nodes™** — As a cost-effective alternative to plastic sheathing, Z-nodes may be used. Specially-shaped zinc anodes, Z-nodes are symmetrically positioned in the outer layer to cathodically protect the cable from corrosion. Used predominantly in anchor line applications, the quantity of anodic zinc used is dependent upon the life expectancy requirement. Z-nodes may be applied to either wire rope or spiral strand designs.

**Poly-Bloc™** — Poly-Bloc is an internal lubricant and blocking compound which is melted and pumped around each wire and into the cable during manufacturing. Poly-Bloc seals the interior of the cable, preventing the intrusion and entrapment of moisture. The use of Poly-Bloc impedes corrosion, rusting and general deterioration.

### Design Options

WWW has engineered a number of unique cable designs, as well as special end termination and attaching methods, to meet individual requirements. Please contact our Engineering Department to discuss your needs.

*For more information on Bethlehem Wire Rope® Structural Assemblies and related end terminations, please refer to our Structural Products catalog.*



**Williamsport Wire Rope Works, Inc.**  
manufacturer of Bethlehem Wire Rope®

100 Maynard Street Post Office Box 3188  
Williamsport Pennsylvania 17701 USA  
telephone: 570-326-5146 facsimile: 570-327-4274  
<http://www.wwwrope.com>



Wire rope products will break if abused, misused or overused. Consult industry recommendations and OSHA Standards before using. Williamsport Wire Rope Works, Inc. warrants all Bethlehem Wire Rope® and Strand products. However, any warranty, expressed or implied as to quality, performance or fitness for use of wire rope products is always premised on the condition that the published breaking strengths apply only to new, unused rope, that the mechanical equipment on which such products are used is properly designed and maintained, that such products are properly stored, handled, used and maintained, and properly inspected on a regular basis during the period of use. Manufacturer shall not be liable for consequential or incidental damages or secondary charges including but not limited to personal injury, labor costs, a loss of profits resulting from the use of said products or from said products being incorporated in or becoming a component of any product. Williamsport Wire Rope Works, Inc. © 2000

